

Date:

Jul 15, 2025

FUZHOU XINYANG ENGINEERING DESIGN CO., Applicant:

ROOM 2X-14J 2# BUILDING HULI ROAD

MAWEI DISTRICT FUZHOU CITY

Attn: 黄工

Sample Description:

One (1) set of submitted sample said to be :

**Epic Playcenter** Item Name

Item No. 2211 Applicant Specified Age 3-6

Grading for Testing

Manufacturer Fuzhou Xinyang Engineering Design Co.,Ltd

Country of Destination

Japan, USA, Europe Jun 09, 2025 & Jul 02, 2025 Date Sample Received Testing Period Jun 09, 2025 to Jul 11, 2025



Tests conducted:

As requested by the applicant, refer to attached page(s) for details.

To be continued







Conclusion:

Tested sample Submitted sample	Standard/Testing Item EN71-1:2014+A1:2018 for mechanical and physical properties	<u>Result</u> Pass
	EN 71-2: 2020 Flammability test	Pass
	EN 71-8: 2018 Safety of Toys - Activity toys for domestic use	Pass
Tested component (16),(17),(18),(19),(20),(21),(22), (23),(24),(25),(26) of submitted sample	EN 71-3:2019+A1:2021 on Migration of Certain Elements	Pass
Other tested component(s) of submitted samples	EN 71-3:2019+A1:2021 on Migration of Certain Elements	Pass#
Tested component (16),(17),(18),(19),(20),(21),(22), (23),(24),(25),(26) of submitted sample	EN 71-3:2019+A2:2024 on Migration of Certain Elements	Pass
Other tested component(s) of	EN 71-3:2019+A2:2024 on Migration of Certain	Pass#

#### Remarks:

# = The submitted samples were not subjected to the scope of the standard. The tests performed as per the

Elements

Authorized by:

For Intertek Testing Services Shenzhen Ltd.

Guangzhou Branch, Hardlines

submitted samples

Victor T.J/ Wang General Manager

> Should you have any query on this report, please click the link below: https://verifyindex.intertek.com.cn/home/index?id=hl\_report\_verify

> > Page 2 of 20







# **Tests Conducted**

#### 1 Physical and Mechanical Tests

As per European Standard on Safety of toys EN71-1:2014+A1:2018

Clause	Testing Items	Assessment
4	General requirements	
4.1	Material	Р
4.2	Assembly	Р
4.3	Flexible plastic sheeting	NA
4.4	Toy bags	NA
4.5	Glass	NA
4.6	Expanding materials	NA
4.7	Edges	Р
4.8	Points and metallic wires	Р
4.9	Protruding parts	NA
4.10	Parts moving against each other	NA
4.11	Mouth actuated toys and other toys intended to be put in the mouth	NA
4.12	Balloons	NA
4.13	Cords of toy kites and other flying toys	NA
4.14	Enclosures	NA
4.15	Toys intended to bear the mass of a child	NA
4.16	Heavy immobile toys	NA
4.17	Projectile toys	NA
4.18	Aquatic toys and inflatable toys	NA
4.19	Percussion caps specifically designed for use in toys and toys using percussion caps	NA
4.20	Acoustics	NA
4.21	Toys containing non-electrical heat source	NA
4.22	Small balls	NA
4.23	Magnets	NA
4.24	Yo-yo balls	NA
4.25	Toys attached to food	NA
4.26	Toy disguise costumes	NA
4.27	Flying toys	NA
5	Toys intended for children under 36 months	
5.1	General requirements	NA
5.2	Soft-filled toys and soft-filled parts of a toy	NA
5.3	Plastic sheeting	NA
5.4	Cords, chains and electrical cables in toys	NA
5.5	Liquid filled toys	NA



Page 3 of 20





# **Tests Conducted**

Clause	Testing Items	Assessment
5.6	Speed limitation of electrically-driven ride-on toys	NA
5.7	Glass and porcelain	NA
5.8	Shape and size of certain toys	NA
5.9	Toys comprising monofilament fibres	NA
5.10	Small balls	NA
5.11	Play figures	NA
5.12	Hemispheric-shaped toys	NA
5.13	Suction cups	NA
5.14	Straps intended to be worn fully or partially around the neck	NA
5.15	Sledges with cords for pulling	NA
6	Packaging	Р
7	Warnings, markings and instructions for use	
7.1	General	Р
7.2	Toys not intended for children under 36 months	P/#
7.3	Latex balloons	NA
7.4	Aquatic toys	NA
7.5	Functional toys	NA
7.6	Hazardous sharp functional edges and points	NA
7.7	Projectile toys	NA
7.8	Imitation protective masks and helmets	NA
7.9	Toy kites	NA
7.10	Roller skates, inlineskates and skateboards and certain other ride-on toys	NA
7.11	Toys intended to be attached to strung across a cradle, cot, or perambulator	NA
7.12	Liquid-filled teethers	NA
7.13	Percussion caps specifically designed for use in toys	NA
7.14	Acoustics	NA
7.15	Toy bicycles	NA
7.16	Toys intended to bear the mass of a child	NA
7.17	Toys comprising monofilament fibres	NA
7.18	Toy scooters	NA
7.19	Rocking horses and similar toys	NA
7.20	Magnetic/electrical experimental sets	NA



Page 4 of 20





#### **Tests Conducted**

Clause	Testing Items	Assessment
7.21	Toys with electrical cables exceeding 300 mm in length	NA
7.22	Toys with cords or chains intended for children of 18 months and over but under 36 months	NA
7.23	Toys intended to be attached to a cradle, cot or perambulator	NA
7.24	Sledges with cords for pulling	NA
7.25	Flying toys	NA
7.26	Improvised projectiles	NA

Remark: P = Pass NA = Not Applicable

# = Age warning statement and indication of hazard was found on the packaging.

Additional information according to the Toy Safety Directives 2009/48/EC requirement. These information also appears as a note within the EN71 but are not standard requirements:

## 1. Marking

The manufacturer's and importer's name, registered trade name or registered trade mark, the address and the CE-marking shall be indicated on the toy or, where that is not possible, on its packaging or in a document accompany the toy. In addition, manufacturers shall ensure that their toys bear a type, batch, serial or model number or other element allowing their identification, or where the size or nature of the toy does not allow it, that the required information is provided on the packaging or in a document accompanying the toy.

	Toy	Packaging
Manufacturer's name	Present	Present
Manufacturer's address	Present	Absent
Importer's name	Absent	Absent
Importer's address	Absent	Absent
Product identification code	Absent	Absent
CE-marking	Absent	Absent

## 2 Flammability Test

Test Standard: European Standard on Safety of Toys EN 71 - 2: 2020

Clause	Testing Items	Assessment
4.1	General requirements	Р
4.2	Toys to be worn on the head	NA
4.3	Toy disguise costumes and toys intended to be worn by a child in play	NA
4.4	Toys intended to be entered by a child	NA
4.5	Soft filled toys	NA

Remark: P = Pass NA = Not Applicable



.

(in)



## **Tests Conducted**

#### 3 Safety Requirement For Activity Toys

Test standard: EN 71-8: 2018, Safety of Toys - Activity toys for domestic use.

Applicant's specified

Age group for testing: 3-6 years Maximum weight of single user: 50kg Maximum total weight: 200kg

Number of samples tested: one (1) set

Clause	Requirement	Result
4.1	General	
4.1.1	Assembly	Р
4.1.2	Static strength	Р
4.1.3	Maximum height	Р
4.1.4	Corners and edges	Р
4.1.5	Protruding parts	Р
4.1.6	Diameter of ropes and other means of suspension	Р
4.1.7	Water accumulation	Р
4.2	Barriers, handrails and ladder and similar means of access to activity toys	
4.2.1	Barriers and handrails preventing a child from falling down	NA
4.2.2	Ladders and similar means of access to activity toys	Р
4.3	Entrapment	
4.3.1	Entrapment of head and neck	Р
4.3.2	Entrapment of clothing and hair	Р
4.3.3	Entrapment of feet	Р
4.3.4	Entrapment of fingers	Р
4.4	Stability of activity toys other than slides, swings and activity toys	
	with crossbeams, and see-saws	
4.4.2	Stability of activity toys with a free height of fall of 600mm or less	NA
4.4.3	Stability of activity toys with a free height of more than 600mm	Р
4.5	Slides	
4.5.2	Stability of slides	Р
4.5.3	Retaining sides for slides	Р
4.5.4	Starting, sliding and run-out sections on slides	Р
4.6	Swings	
4.6.1.2	Swings and other activity toys with crossbeams more than 1200mm over the ground	Р
4.6.1.3	Swings and other activity toys with crossbeams 1 200 mm or less above the ground	NA



Page 6 of 20





# **Tests Conducted**

Clause	Requirement	Result
4.6.2	Static strength of crossbeams, swing devices and suspension connectors	Р
4.6.3	Swings intended for children under 36 months	NA
4.6.4	Minimum clearance between adjacent swing elements, and adjacent structures	Р
4.6.5	Lateral stability of swing elements	P
4.6.6	Minimum clearance between swing elements and the ground	Р
4.6.7	Suspension connectors and swing devices	Р
4.6.8	Impact, geometry and design of swing elements	P
4.7	See-saws	
4.7.1	Stability of see-saws	NA
4.7.2	Seat/stand height	NA
4.7.3	Restraint of motion	NA
4.7.4	Pinching and crushing of fingers and toes	NA
4.7.5	Hand supports	NA
4.8	Carousels and rocking activity toys	NA
4.9	Paddling pools	
4.9.1	Static strength of paddling pools with non-inflatable walls	NA
4.9.2	Paddling pools with inflatable walls	NA
5	Warnings, markings, and instructions	
5.1.1	General	Р
5.1.2	Paddling pools	NA
5.2	Assembly and installation instructions	Р
5.3	Maintenance	Р

Abbreviation: P = Pass NA = Not applicable



intertek.com





#### **Tests Conducted**

#### EN 71-3:2019+A1:2021 on Migration of Certain Elements 4

## (A) Test Result

With reference to EN 71-3:2019+A1:2021 and followed by Inductively Coupled Plasma Atomic Emission Spectrometry, Inductively Coupled Argon Mass Spectrometry, Ion Chromatography- Inductively Coupled Plasma-Mass Spectrometry, Ion Chromatography with UV-VIS and Gas Chromatographic - Mass Spectrometry.

Category (III): Scraped-off toy material

		Res		<u>Detection</u>	Limit		
Element	1	Teste 2	<u>Limit</u> (mg/kg)	(mg/kg)			
Aluminium (AI)	ND	ND	3 ND	<b>5</b> ND	6 ND	300	28130
Antimony (Sb)	15	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	ND	10	47
Barium (Ba)	50	ND	11	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	ND	5	17
Chromium (III) (Cr(III)) #	ND	ND	ND	ND	ND	10	460
Chromium (VI) (Cr(VI))	ND	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	ND	2.5	180000
Organic tin **	ND	ND	ND	ND	ND	5	12
Zinc (Zn)	18,200	6,490	1,190	ND	ND	100	46000



Page 8 of 20







# **Tests Conducted**

		Res		<u>Detection</u>	Limit		
<u>Element</u>	Tested Component					Limit	<u>Limit</u> (mg/kg)
	7	8	9	10	11	(mg/kg)	<u>,g/g/</u>
Aluminium (Al)	ND	ND	ND	ND	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	ND	5	17
Chromium (III) (Cr(III)) #	ND	ND	ND	ND	ND	10	460
Chromium (VI) (Cr(VI))	ND	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	ND	2.5	180000
Organic tin **	ND	ND	ND	ND	ND	5	12
Zinc (Zn)	ND	ND	ND	ND	ND	100	46000



Page 9 of 20





# **Tests Conducted**

		Res	<u>Detection</u>	<u>Limit</u>			
<u>Element</u>		Teste	Limit	(mg/kg)			
	12	13	14	15	16	(mg/kg)	<del>- 3-37</del>
Aluminium (Al)	ND	ND	ND	ND	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	ND	5	17
Chromium (III) (Cr(III)) #	ND	ND	ND	ND	ND	10	460
Chromium (VI) (Cr(VI))	ND	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	29	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	ND	2.5	180000
Organic tin **	ND	ND	ND	ND	ND	5	12
Zinc (Zn)	ND	ND	ND	ND	122	100	46000



Page 10 of 20







# **Tests Conducted**

		Res		Detection	Limit		
<u>Element</u>		Teste	Limit	<u>Limit</u> (mg/kg)			
	17	18	19	20	21	(mg/kg)	<u> </u>
Aluminium (Al)	ND	ND	ND	ND	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	ND	5	17
Chromium (III) (Cr(III)) #	ND	ND	ND	ND	ND	10	460
Chromium (VI) (Cr(VI))	ND	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	ND	2.5	180000
Organic tin **	ND	ND	ND	ND	ND	5	12
Zinc (Zn)	ND	ND	ND	ND	ND	100	46000



Page 11 of 20





#### **Tests Conducted**

		Res	Detection	<u>Limit</u>			
<u>Element</u>		Teste		Limit	(mg/kg)		
	22	23	24	25	26	(mg/kg)	<del>1 3 37</del>
Aluminium (Al)	ND	ND	ND	ND	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	ND	5	17
Chromium (III) (Cr(III)) #	ND	ND	ND	ND	ND	10	460
Chromium (VI) (Cr(VI))	ND	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	ND	2.5	180000
Organic tin ++	ND	ND	ND	ND	ND	5	12
Zinc (Zn)	ND	ND	ND	ND	ND	100	46000

Remark: mg/kg = milligram per kilogram

++ = Unless the test results were marked with "Δ", organic tin contents were not directly determined and were derived from migration results of total tin.

Organic tin test result was expressed as tributyl tin.

ND = Not detected (less than detection limit)

# = The reported value of migration of chromium (III) = migration value of total chromium -

migration value of chromium (VI).  $\Delta$  = Confirmation test was performed on the tested component. The reported value was the sum of the migration values of dimethyl tin, methyl tin, butyl tin, dibutyl tin, tributyl tin, tetrabutyl tin, n-octyl tin, di-n-octyl tin, di-n-propyl tin, diphenyl tin and triphenyl tin after converted to tributyl tin by calculation. Other organic tin compounds may also be present in sample as stated in EN 71-3:2019+A1:2021.

 $\nabla$  = The result is based on dry weight of testing sample.

Tested component(s): See component list in the last section of this report









## **Tests Conducted**

(B) Categories of various toy materials

Category I: Dry, brittle, powder like or pliable

Solid toy material from which powder-like material is released during playing and semi-solid materials that may also leave residues on the hands during play. The material can be ingested. Contamination of the hands with the material may contribute to the oral exposure of the material (e.g. the cores of colouring pencils, chalk, crayons, modelling clays and plaster).

Category II: Liquid or sticky

Fluid or viscous toy material, which can be ingested or to which dermal exposure may occur during playing (e.g. liquid paints, finger paints, liquid ink in pens, glue sticks, slimes, bubble solution).

Category III: Scraped-off

Solid toy material with or without a coating, which can be ingested as a result of biting, tooth scraping, sucking or licking (e.g. coatings, lacquers, plastics, paper, textiles, glass, ceramic, metallic, wooden, bone, leather and other materials).



Page 13 of 20





**Tests Conducted** 

#### 5 EN 71-3:2019+A2:2024 on Migration of Certain Elements

With reference to EN 71-3:2019+A2:2024 and followed by Inductively Coupled Plasma Atomic Emission Spectrometry, Inductively Coupled Argon Mass Spectrometry, Ion Chromatography- Inductively Coupled Plasma-Mass Spectrometry, Ion Chromatography with UV-VIS and Gas Chromatographic - Mass Spectrometry. Category (III): Scraped-off toy material

Took Itam			Result		11-24-	<b>.</b>	1		
Test Item	1	2	3	5	6	Units	D.L.	Limit	
Aluminium (Al)	ND	ND	ND	ND	ND	mg/kg	300	28130	
Antimony (Sb)	15	ND	ND	ND	ND	mg/kg	10	560	
Arsenic (As)	ND	ND	ND	ND	ND	mg/kg	10	47	
Barium (Ba)	50	ND	11	ND	ND	mg/kg	10	18750	
Boron (B)	ND	ND	ND	ND	ND	mg/kg	50	15000	
Cadmium (Cd)	ND	ND	ND	ND	ND	mg/kg	5	17	
Chromium (III) (Cr III)#	ND	ND	ND	ND	ND	mg/kg	10	460	
Chromium (VI) (Cr VI)	ND	ND	ND	ND	ND	mg/kg	0.025	0.053	
Cobalt (Co)	ND	ND	ND	ND	ND	mg/kg	10	130	
Copper (Cu)	ND	ND	ND	ND	ND	mg/kg	10	7700	
Lead (Pb)	ND	ND	ND	ND	ND	mg/kg	10	23	
Manganese (Mn)	ND	ND	ND	ND	ND	mg/kg	10	15000	
Mercury (Hg)	ND	ND	ND	ND	ND	mg/kg	10	94	
Nickel (Ni)	ND	ND	ND	ND	ND	mg/kg	10	930	
Selenium (Se)	ND	ND	ND	ND	ND	mg/kg	10	460	
Strontium (Sr)	ND	ND	ND	ND	ND	mg/kg	100	56000	
Tin (Sn)	ND	ND	ND	ND	ND	mg/kg	2.5	180000	
Organic tin++	ND	ND	ND	ND	ND	mg/kg	5	12	
Zinc (Zn)	18,200	6,490	1,190	ND	ND	mg/kg	100	46000	



Page 14 of 20





# **Tests Conducted**

Took Itom			Result		l luita	D.1	Limit		
Test Item	7	8	9	10	11	Units	D.L.	Limit	
Aluminium (Al)	ND	ND	ND	ND	ND	mg/kg	300	28130	
Antimony (Sb)	ND	ND	ND	ND	ND	mg/kg	10	560	
Arsenic (As)	ND	ND	ND	ND	ND	mg/kg	10	47	
Barium (Ba)	ND	ND	ND	ND	ND	mg/kg	10	18750	
Boron (B)	ND	ND	ND	ND	ND	mg/kg	50	15000	
Cadmium (Cd)	ND	ND	ND	ND	ND	mg/kg	5	17	
Chromium (III) (Cr III)#	ND	ND	ND	ND	ND	mg/kg	10	460	
Chromium (VI) (Cr VI)	ND	ND	ND	ND	ND	mg/kg	0.025	0.053	
Cobalt (Co)	ND	ND	ND	ND	ND	mg/kg	10	130	
Copper (Cu)	ND	ND	ND	ND	ND	mg/kg	10	7700	
Lead (Pb)	ND	ND	ND	ND	ND	mg/kg	10	23	
Manganese (Mn)	ND	ND	ND	ND	ND	mg/kg	10	15000	
Mercury (Hg)	ND	ND	ND	ND	ND	mg/kg	10	94	
Nickel (Ni)	ND	ND	ND	ND	ND	mg/kg	10	930	
Selenium (Se)	ND	ND	ND	ND	ND	mg/kg	10	460	
Strontium (Sr)	ND	ND	ND	ND	ND	mg/kg	100	56000	
Tin (Sn)	ND	ND	ND	ND	ND	mg/kg	2.5	180000	
Organic tin++	ND	ND	ND	ND	ND	mg/kg	5	12	
Zinc (Zn)	ND	ND	ND	ND	ND	mg/kg	100	46000	



Page 15 of 20

Tel inte





# **Tests Conducted**

Test Item			Result		Units	D.L.	Limit	
rest item	12	13	14	15	16	Units	D.L.	Limit
Aluminium (AI)	ND	ND	ND	ND	ND	mg/kg	300	28130
Antimony (Sb)	ND	ND	ND	ND	ND	mg/kg	10	560
Arsenic (As)	ND	ND	ND	ND	ND	mg/kg	10	47
Barium (Ba)	ND	ND	ND	ND	ND	mg/kg	10	18750
Boron (B)	ND	ND	ND	ND	ND	mg/kg	50	15000
Cadmium (Cd)	ND	ND	ND	ND	ND	mg/kg	5	17
Chromium (III) (Cr III)#	ND	ND	ND	ND	ND	mg/kg	10	460
Chromium (VI) (Cr VI)	ND	ND	ND	ND	ND	mg/kg	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	ND	mg/kg	10	130
Copper (Cu)	ND	ND	ND	ND	ND	mg/kg	10	7700
Lead (Pb)	ND	ND	ND	ND	ND	mg/kg	10	23
Manganese (Mn)	ND	ND	29	ND	ND	mg/kg	10	15000
Mercury (Hg)	ND	ND	ND	ND	ND	mg/kg	10	94
Nickel (Ni)	ND	ND	ND	ND	ND	mg/kg	10	930
Selenium (Se)	ND	ND	ND	ND	ND	mg/kg	10	460
Strontium (Sr)	ND	ND	ND	ND	ND	mg/kg	100	56000
Tin (Sn)	ND	ND	ND	ND	ND	mg/kg	2.5	180000
Organic tin++	ND	ND	ND	ND	ND	mg/kg	5	12
Zinc (Zn)	ND	ND	ND	ND	122	mg/kg	100	46000



Page 16 of 20





# **Tests Conducted**

Test Item			Result		Units	D.L.	Limit		
rest item	17	18	19	20	21	Units	D.L.	Lillin	
Aluminium (AI)	ND	ND	ND	ND	ND	mg/kg	300	28130	
Antimony (Sb)	ND	ND	ND	ND	ND	mg/kg	10	560	
Arsenic (As)	ND	ND	ND	ND	ND	mg/kg	10	47	
Barium (Ba)	ND	ND	ND	ND	ND	mg/kg	10	18750	
Boron (B)	ND	ND	ND	ND	ND	mg/kg	50	15000	
Cadmium (Cd)	ND	ND	ND	ND	ND	mg/kg	5	17	
Chromium (III) (Cr III)#	ND	ND	ND	ND	ND	mg/kg	10	460	
Chromium (VI) (Cr VI)	ND	ND	ND	ND	ND	mg/kg	0.025	0.053	
Cobalt (Co)	ND	ND	ND	ND	ND	mg/kg	10	130	
Copper (Cu)	ND	ND	ND	ND	ND	mg/kg	10	7700	
Lead (Pb)	ND	ND	ND	ND	ND	mg/kg	10	23	
Manganese (Mn)	ND	ND	ND	ND	ND	mg/kg	10	15000	
Mercury (Hg)	ND	ND	ND	ND	ND	mg/kg	10	94	
Nickel (Ni)	ND	ND	ND	ND	ND	mg/kg	10	930	
Selenium (Se)	ND	ND	ND	ND	ND	mg/kg	10	460	
Strontium (Sr)	ND	ND	ND	ND	ND	mg/kg	100	56000	
Tin (Sn)	ND	ND	ND	ND	ND	mg/kg	2.5	180000	
Organic tin++	ND	ND	ND	ND	ND	mg/kg	5	12	
Zinc (Zn)	ND	ND	ND	ND	ND	mg/kg	100	46000	



\_





#### **Tests Conducted**

Took Itom			Result		l leite	D.I	l imais		
Test Item	22	23	24	25	26	Units	D.L.	Limit	
Aluminium (Al)	ND	ND	ND	ND	ND	mg/kg	300	28130	
Antimony (Sb)	ND	ND	ND	ND	ND	mg/kg	10	560	
Arsenic (As)	ND	ND	ND	ND	ND	mg/kg	10	47	
Barium (Ba)	ND	ND	ND	ND	ND	mg/kg	10	18750	
Boron (B)	ND	ND	ND	ND	ND	mg/kg	50	15000	
Cadmium (Cd)	ND	ND	ND	ND	ND	mg/kg	5	17	
Chromium (III) (Cr III)#	ND	ND	ND	ND	ND	mg/kg	10	460	
Chromium (VI) (Cr VI)	ND	ND	ND	ND	ND	mg/kg	0.025	0.053	
Cobalt (Co)	ND	ND	ND	ND	ND	mg/kg	10	130	
Copper (Cu)	ND	ND	ND	ND	ND	mg/kg	10	7700	
Lead (Pb)	ND	ND	ND	ND	ND	mg/kg	10	23	
Manganese (Mn)	ND	ND	ND	ND	ND	mg/kg	10	15000	
Mercury (Hg)	ND	ND	ND	ND	ND	mg/kg	10	94	
Nickel (Ni)	ND	ND	ND	ND	ND	mg/kg	10	930	
Selenium (Se)	ND	ND	ND	ND	ND	mg/kg	10	460	
Strontium (Sr)	ND	ND	ND	ND	ND	mg/kg	100	56000	
Tin (Sn)	ND	ND	ND	ND	ND	mg/kg	2.5	180000	
Organic tin++	ND	ND	ND	ND	ND	mg/kg	5	12	
Zinc (Zn)	ND	ND	ND	ND	ND	mg/kg	100	46000	

#### Remarks:

D.L. = Detection Limit

- ++ = Unless the test results were marked with " $\Delta$ ", Organic tin contents were not directly determined and were derived from migration results of total tin.
- Organic tin test result was expressed as tributyl tin.

ND = Not detected

# = The reported value of migration of Chromium (III) = migration value of total Chromium – migration value of Chromium(VI).

### Categories of various toy materials

Category I: Dry, brittle, powder like or pliable

Solid toy material from which powder-like material is released during playing and semi-solid materials that may also leave residues on the hands during play. The material can be ingested. Contamination of the hands with the material may contribute to the oral exposure of the material. (e.g. the cores of colouring pencils, chalk, crayons, modelling clays and plaster).



Tel +8620 28209114 intertek.com.cn intertek.com



Intertek Testing Services Shenzhen Limited, Guangzhou Branch 深圳天祥质量技术服务有限公司广州分公司

111, Huichuang Kongjian, TCL Cultural Industrial Park, No.69, Guangpu Road, Huangpu District, Guangzhou, Guangdong, China. / Room 401/501/601/801/901/1003, No. 8, East BaoYing Road, Huangpu District, Guangzhou, China



**Tests Conducted** 

Category II: Liquid or sticky

Fluid or viscous toy material, which can be ingested or to which dermal exposure may occur during playing. (e.g. liquid paints, finger paints, liquid ink in pens, glue sticks, slimes, bubble solution).

Category III: Scraped-off

Solid toy material with or without a coating, which can be ingested as a result of biting, tooth scraping, sucking or licking. (e.g. coatings, lacquers, plastics, paper, textiles, glass, ceramic, metallic, wooden, bone, leather and other materials).

Tested Components: See component list in the last section of this report.

## **Component List**

No.	Test Component Description(s)	
(1)	Dark green coating on metal (surface of corner of frame of swing).	
(2)	Yellow coating on metal (surface of corner of frame of swing).	
(3)	Orange coating on wood (surface of platform, frame of swing).	
(4)	@ Black coating on metal (letter of information plate).	
(5)	Yellow plastic (handle of platform).	
(6)	Dull yellow plastic (step of climbing ladder).	
(7)	Dull blue plastic (step of climbing ladder).	
(8)	Yellow plastic (slide).	
(9)	Black plastic (ring of hook of swing).	
(10)	White soft plastic (cover of hook of swing).	
(11)	Milky white plastic (ring of strap of swing).	
(12)	Ginger soft plastic (seat of swing).	
(13)	Yellow soft plastic (ring of seat of swing).	
(14)	Natural color wood with black printing (platform, frame of swing).	
(15)	White cord (strap of swing).	



Page 19 of 20





**Tests Conducted** 

#### **Component List**

No.	Test Component Description(s)
(16)	Yellow plastic (telescope).
(17)	Red plastic (telescope).
(18)	Transparent plastic (lens of telescope).
(19)	Dark yellow plastic (holder of telescope).
(20)	Grey plastic (impounding reservoir).
(21)	Dark blue plastic (faucet).
(22)	White plastic (faucet).
(23)	Milky white plastic (joint of faucet).
(24)	Semi-transparent white soft plastic (washer of faucet).
(25)	Cyan blue plastic (wash basin).
(26)	Deep yellow plastic (steering wheel of platform).

②: Since the sample weight of the component was less than 10 mg, soluble heavy metal analysis was not applicable.

End of report

The statements of conformity reported have considered the decision rule agreed, namely that Intertek have taken account of measurement uncertainty as calculated by Intertek, and applied according to ILAC-G8/09:2019 (Non-binary acceptance based on guard band  $\mathbf{w} = \mathbf{U}$ ) except designation from the customer, regulation or test specification. This decision rule only applies to the numeric test results.

The sample(s) and sample information hereto are provided by the client who shall be solely responsible for the authenticity and integrity thereof. The results shown in this report relate only to the sample(s) tested. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. This report shall not be reproduced unless with prior written approval from Intertek Testing Services Shenzhen Limited, Guangzhou Branch.



i age 20 oi

